



ALTA® Commercial Specs

Commercial Breathable Housewrap

Roll Dimensions (ft) W x L		9' x 100', 9' x 150' 10' x 100', 10' x 150'	ESR -#1108 02/16
PHYSICAL PROPERTY		TEST METHOD	ALTA® 360 Commercial Properties
Basis Weight	grams/m ²	ASTM D 3776	82
Thickness	mils	ASTM D 3776	8
Gurley Air Porosity	sec	TAPPI T-460	>2000
Water Resistance	cm	AATCC 127	>300
1" Tensile, lbs	MD	ASTM D 882	30
	CD		30
Trapezoid Tear, lbs	MD	ASTM D-1117	13.5
	CD		12.5
MVTR	PERMS	ASTM E-96, method A	35
UV Light Exposure		Aging Test	180 Days
Drainage Efficiency Test		ASTM - 2273	>95%
Flammability		ASTM - E-84	Class A

The information contained herein is furnished without charge or obligation and the recipient assumes all responsibility for its use. Because conditions of use and handling may vary and are beyond our control, we make no representation about, and are not responsible or liable for, the accuracy or reliability of said information or the performance of any product. Any specifications, properties or applications listed herein are provided as information only and in no way modify, amend, enlarge or create any warranty. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. CLAF® is a registered trademark of ANCI, Inc.



AMERICAS | ANCI, Inc.
+1-404-891-1300
sales@anciglobal.com

EMEA | ANCI, SAS
+32 442-277-624
sales.europe@anciglobal.com

ASIA | ENEOS Techno
Materials
+81-3-5617-4920

www.anciglobal.com